

CHROME BAR

Typical Analysis (Ave. values %)		С	Si	Mn	Cr	Мо	V	S	Р
	4140 Chrome Bar	0.40	0.2	0.8	1.0	0.2	-	0.03	0.03
	1045 Chrome Bar	0.45	0.3	0.7				0.03	0.03
	20MnV6 Chrome Bar	0.18	0.3	1.5	-	-	0.15	0.03	0.03
	38Mn Vs6 Induction hardened Chrome Bar	0.37	0.48	1.40	0.30	0.08	0.14		

DESCRIPTION	4140 Chrome Bar	Low alloy general purpose high tensile hardened and tempered steel. Ideal material for highly stressed component applications.
	1045 Chrome Bar	Fully Killed medium carbon steel. The traditional product used in the manufacture of hard chrome bar.
	20MnV6 Chrome Bar	Vanadium micro alloyed steel grade with higher yield point, excellent weldability and impact strength.
	38Mn Vs6 Induction hardened Chrome Bar	An induction hardened hard chrome plated bar designed to withstand mechanical damage.

STORAGE & HANDLING

The Chrome plated bars can easily be damaged, therefore they are delivered protected by packaging in cardboard or plastic tubes. It is necessary to follow several precautions while handling the product between delivery and final production

- ➤ **Handling** During handling, never use steel chains, always use canvas or plastic belts, fork lift tynes must be lined with wood or plastic material.
- Cutting Leave the bar in its protective sleeve and cut dry, cutting emulations containing water can be absorbed in the sleeve and cause erosion. Vice jaws must be lined with plastic or wood.
- ➤ **Storage** Chromed bars must be stored in dry conditions and not exposed to the sun light. Direct contact with the floor should be avoided.

APPLICATIONS

Standard cylinders, Dump trucks, Fork lifts, Presses, Gates and Automatic doors, Tractors, Steering- Gear systems, Robots, Lifts, Hydraulic platforms, Machines for agriculture, Heavy duty cylinders, Cranes, Drilling equipment, Garbage compactors.

HARD CHROME	Surface hardness	800-1000 HV (64-69 RC)



AUSTRALIA

PLATING	Surface smoothness	0.10-0.30 μm Ra
	Surface deposit	0.025-0.050 mm

INDUCTION HARDENING	The hardened outer layer results in greater strength and resistance to mechanical damage. Case hardness 55-56 R/C before plating.				
	<u>Dia mm</u>	Case depth mm			
	12-20	1.0 +/-0.5			
	>20-40	1.5 +/-0.5			
	>40-80	2.0 +/-0.5			
	>80-120	2.5 +/-0.5			

TOLERANCES	Diameter	According to ISO f7 20-30 mm0.020 / -0.041 30-50 mm0.025 / -0.050 50-80 mm0.030 / -0.060 80-120 mm0.036 / -0.071
	Straightness	< 0.5 mm / 2000 mm
	Out of roundness	<1/2 of ISO f7 field
	Concentricity	+/- 3 μm
	Surface roughness	Ra 0.2 μm max. Rt 3.0 μm max.
	Bearing ratio	> 50% (at depth of 0.15 µm)

MECHANICAL PROPERTIES		Tensile Strength MPa	Yield Strength MPa	Elong. %
	4140 Chrome Bar	900-1150	>735	>14
	1045 Chrome Bar	580-800	>340	>17
	20MnV6 Chrome Bar	550-700	>440	>19
	38Mn Vs6 Induction hardened Chrome Bar	800-950	>520	>12



AUSTRALIA

WELDING

During welding the chromed bar must be protected against overheating and splatter. Strength properties of the joint will not be the same as the base metal.

Filler metal: 4140 (FOX CM2-KB electrodes or CM2-IGwire),

1045 & 20MnV6 (FOX EV50),

For advice in connection with welding, please consult our engineers.

SIZE RANGE	4140 4140 Induction hardened	19.05 to 101.6 mm 25.40 to 95.25 mm
	1045 1045 Induction hardened	12.00 to 171.45 mm 25.40 to 127 mm
	20MnV6 Chrome Bar	12.00 to 101.60 mm
	38Mn Vs6	31.75 to 114.3 mm

<u>LOCATIONS</u>						
Bohler Uddeholm Australia Pty Ltd ABN 15000013052						
Sydney	129-135 McCredie Rd Guildford	2161	Ph (02) 8724 5554	Fax (02) 8724 5555		
Newcastle	3 Pavilion PI Cardiff	2285	Ph (02) 4954 6611	Fax (02) 4956 5773		
Albury	1 Eames St Albury	2640	Ph (02) 6041 3399	Fax (02) 6041 1820		
Wollongong	40 Doyle Ave Unanderra	2526	Ph (02) 4272 6544	Fax (02) 4272 7563		
Marayong	1/21 Binney Rd Marayong	2148	Ph (02) 9831 4431	Fax (02) 9671 1682		
Melbourne	282-290 Greens Rd Dandenong	3175	Ph (03) 9767 5554	Fax (03) 9767 5555		
Bayswater	4 Amsted Rd Bayswater	3153	Ph (03) 9739 8022	Fax (03) 9739 8033		
Adelaide	1 Williams Cir Pooraka	5095	Ph (08) 8368 4554	Fax (08) 8368 4555		
Brisbane	12-18 Limestone St Darra	4076	Ph (07) 3712 9554	Fax (07) 3712 9555		
Townsville	9-11 Caldwell St Garbutt	4814	Ph (07) 4479 4800	Fax (07) 4725 1316		
Mackay	19-21 Iridium Dr	4740	Ph 0414 718565			
Perth	29-33 Gauge Cir Canningvale	6155	Ph (08) 9455 8672	Fax (08) 9455 8673		
Kewdale	5 Beete St Welshpool	6106	Ph (08) 9350 9582	Fax (08) 9350 9683		
Launceston	20 Murphy St Invermay	7248	Ph (03) 6334 3542	Fax (03) 6331 4001		
	,					

www.buau.com.au

Every care has been taken in listing this information, particularly specifications. Bohler Uddeholm Australia Pty Ltd will not accept responsibility for any loss or other damage caused to any person or Company as a result of the use of information contained herein